


## Sales Data Sheet

# Infill for Artificial Turf Systems



### Ecore A-R | Black EPDM Alternative-Rubber Infill

- A non-SBR, virgin rubber infill
- Little to no dust, not oily, odorless
- No agglomeration or stability loss up to 335F
- Resists abrasion and excessive wear
- Consistent particles
- Consistent chemistry
- Manufactured in the United States
- 100% recyclable
- 24.5 lbs./ft<sup>3</sup> nominal
- Size: 8-18 mesh

### Ecore A-R Test Results

Metal	EN 71-3 Migration Limits (mg/kg)	Result (mg/kg)
Cadmium	23	None Detected
Lead	160	None Detected
Mercury	94	None Detected
Barium	56,000	0.8
Chromium	460	0.76
Hexavalent Chromium	0.2	None Detected
Arsenic	47	None Detected
Selenium	460	None Detected

### Green & Tan | EPDM Alternative-Rubber Infill

- A non-SBR, virgin rubber infill
- Little to no dust, not oily, odorless
- No agglomeration or stability loss up to 335F
- Resists abrasion and excessive wear
- Consistent particles
- Consistent chemistry
- Manufactured in the United States
- 100% recyclable
- 41 lbs./ft<sup>3</sup> nominal
- Size: 1.0-3.5mm nominal

### Green & Tan Test Results

Metal	EN 71-3 Migration Limits (mg/kg)	Result (mg/kg)
Cadmium	23	None Detected
Lead	160	0.485
Mercury	94	0.0145
Barium	56,000	14.4
Chromium	460	3.06
Hexavalent Chromium	0.2	None Detected
Arsenic	47	None Detected
Selenium	460	None Detected